

# CL-200-XSR

MADICO PROTEKT™ FILM

**Benefits:**


- Reduced fading of interior furnishings by screening out destructive UV rays
- Increased safety by helping hold shattered glass together
- Clear, non-tinted appearance
- Improved security by creating a deterrent to forced entry
- Enhanced appearance with distinctive, stylish look

**Performance Data:**

<b>Total Solar Energy:</b>	
Transmitted	78%
Reflected	10%
Absorbed	12%
<b>Visible Light:</b>	
Transmitted	85%
Reflected	10%
<b>“U” Factor:</b>	
Median	1.08
Design	1.12
<b>Ultra Violet Light Rejected</b>	
	99%
<b>Shading Coefficient</b>	
	.93
<b>Total Solar Energy Rejected</b>	
	19%

**Physical Properties:**

<b>Film Thickness</b>	.002"
<b>Structure</b>	Single-Ply
<b>Tensile Strength</b>	32,000 PSI Avg. MD/TD
<b>Break Strength</b>	50 Pounds Per Inch (Width)
<b>Adhesive Type</b>	Acrylic Pressure Sensitive
<b>Peel Strength</b>	5 to 6 Pounds Per Inch



ISO 9001: 2000 Certified

45 Industrial Parkway, Woburn, MA 0180 • 800-225-1926 • www.madico.com

Since only the user is aware of the specific condition in which the product is to be used, it is the user's responsibility to determine whether the product is suitable for that intended use. If the specific conditions of use are critically dependent on any of the properties of the product, or if you need further information of any sort, contact Madico or your local Madico window film dealer.