

Madico Standard Solar Films Data

Product	Description	Visible Light Transmitted	Visible Light Reflected	Total Solar Energy Transmitted	Solar Energy Reflectance	Solar Energy Absorbance	Total Solar Energy Rejected	UV Rejection	Solar Heat Gain Coefficient	Glare Reduction
SRS 220	Silver	15%	55%	11%	48%	41%	78%	99%	0.22	83%
SRS 330	Silver	25%	43%	18%	46%	36%	73%	99%	0.28	72%
RS 440	Silver	36%	42%	24%	40%	36%	66%	99%	0.33	59%
SB 221	Bronze	20%	33%	15%	42%	43%	75%	99%	0.25	77%
SB 341	Bronze	40%	25%	25%	35%	40%	66%	99%	0.34	55%
TSG 335	Neutral	40%	17%	38%	22%	40%	53%	99%	0.47	55%
SRS 220 EXSR	Exterior Silver	15%	55%	11%	48%	41%	78%	99%	0.22	83%
SRS 330 EXSR	Exterior Silver	25%	43%	18%	46%	36%	73%	99%	0.28	72%
SG 220 EXSR	Exterior Gray	24%	28%	21%	26%	53%	65%	99%	0.35	73%
SB 221 EXSR	Exterior Bronze	20%	33%	15%	42%	43%	75%	99%	0.25	77%