

SunscapeSelect[®] Product Data

Product	Description	Visible Light Transmitted	Visible Light Reflected	Solar Energy Transmitted	Solar Energy Reflectance	Solar Energy Absorbance	Total Solar Energy Rejected	Median "U" Factor	Design "U" Factor	Shading Coefficient	UV Rejection	Solar Heat Gain Coefficient	Glare Reduction
DG-35	Designer Gray	38%	20%	33%	23%	44%	56%	1.0	1.04	0.51	>99%	0.44	57%
DG-45	Designer Gray	42%	13%	40%	15%	45%	49%	1.06	1.1	0.58	>99%	0.50	52%
DG-55	Designer Gray	51%	11%	47%	14%	39%	43%	1.07	1.11	0.66	>99%	0.57	42%
SL-180	Starlite	8%	55%	6%	53%	41%	83%	1.06	1.1	0.19	>99%	0.17	91%
SL-280	Starlite	28%	33%	23%	35%	42%	66%	1.02	1.06	0.39	>99%	0.34	68%
SL-380	Starlite	37%	21%	32%	22%	46%	53%	1.09	1.13	0.54	>99%	0.47	58%
SB-25	Soft Bronze	17%	37%	12%	45%	43%	78%	0.9	0.95	0.26	>99%	0.23	81%
SB-35	Soft Bronze	37%	22%	30%	29%	41%	63%	0.93	0.98	0.42	>99%	0.37	58%
DG-35 4Mil	Designer Gray	38%	20%	33%	23%	44%	56%	1.0	1.04	0.51	>99%	0.44	57%
DG-45 4Mil	Designer Gray	42%	13%	40%	15%	45%	49%	1.06	1.1	0.58	>99%	0.50	52%
DG-35 8Mil	Designer Gray	38%	20%	33%	23%	44%	56%	1.0	1.04	0.51	>99%	0.44	57%
DG-45 8Mil	Designer Gray	42%	13%	40%	15%	45%	49%	1.06	1.1	0.58	>99%	0.50	52%
SL-180 EXSR	Starlite, Exterior	8%	55%	6%	53%	41%	83%	1.06	1.1	0.19	>99%	0.17	91%

All solar optical properties taken on 1/8" glass.

Since only the user is aware of the specific conditions in which the product is to be used, it is the user's responsibility to determine whether the product is suitable for that intended use. If the specific conditions of use are critically dependent on any of the properties of the product, or if you need further information of any sort, contact Madico or your local Madico window film dealer.