

Product Specifications

Film Performance	Hüper Ceramic 30	Hüper Ceramic 40	Hüper Ceramic 50	Hüper Ceramic 60	Hüper Acht	Hüper Sech	Hüper Drei
Visible Light Transmission %	30	42	49	58	77	60	36
Visible Light Reflectance %	11.0	9.02	10.2	9.06	9.0	8.28	12.24
Ultra Violet Rejection %	99.9	99.9	99.9	99.9	99.9	99.9	99.9
Infrared Rejection %	86	80	68	60	77	82	98
Shading Coefficient	0.43	0.53	0.62	0.65	0.63	0.54	0.37
Solar Heat Gain Coefficient	0.37	0.46	0.53	0.56	0.46	0.46	0.32
Total Solar Energy Rejected %	63	56	50	43	46	54	70

* All performance information is calculated using the definitions and equations in the ISO9050 & ASHRAE Handbooks